


Flexibility comparison



Test method (Toyox standard test)
 The sample hose is compressed and bent as shown below and the load (N) is checked for each set span.
 • Compression speed: 200 mm/min
 • Sample hose (25 ϕ) length: 1 m

